



STOCK NO. 7860062

March, 2013

AQUABARRIER™ TWF – 24"

AquaBarrier™ TWF is made by integrally bonding a high density cross-woven polyethylene film to SBS modified rubberized asphalt. It is a cold-applied, self-adhering building envelope membrane designed to be used as a through wall flashing system. AquaBarrier™ TWF is used in adhered flashing application directly over masonry, concrete, gypsum, wood or metal substrates which have been properly primed. The surface film of AquaBarrier™ TWF is over 40% thicker than the regular AquaBarrier™ AVB & FP surface films, making it ideal for more demanding applications where higher tensile and puncture resistance are required. The release film is a silicone treated paper, which is easily removed prior to product installation. IKO's products are produced and designed with consideration for environmental responsibility and sustainability, manufactured in facilities that comply with the most stringent government environmental regulations, and can therefore be a part of any "green" construction project.

CHARACTERISTIC	UNITS	NOMINAL VALUE	TEST METHOD	STANDARD LIMITS	
QUANTITY PER PALLET:	-	25	-	N/A	
PALLET SIZE:	cm (in)	119 x 119 (47 x 47)	-	-	
LENGTH:	m (ft)	22.9 (75)	-	± 1%	
WIDTH:	mm (in)	610 (24)	-	± 3 (1/8)	
THICKNESS:	mm (mils)	1.2 (47)	ASTM D5147	± 0.4 (16)	
FILM THICKNESS:	mm (mils)	0.3 (12)	ASTM D5147	-	
COLD FLEX:	°C (°F)	> -29 (-20)	ASTM D1970	MIN: -15 (5)	
TENSILE STRENGTH	MD: XD:	kN/m (lbsf/in)	20 (115) 20 (115)	ASTM D412	-
ULTIMATE ELONGATION	MD: XD:	%	> 65* > 65*	ASTM D412	-
TEAR STRENGTH	MD: XD:	N (lbf)	260 (59) 240 (54)	ASTM D5601	-
TENSILE-TEAR	MD: XD:	N (lbs)	700 (158) 700 (158)	ASTM D4073	-
PEEL RESISTANCE:		Kg/mm(lb/in)	0.2 (10.8)	ASTM D903	-
PEEL RESISTANCE	MD: XD:	Kg/mm(lb/in)	0.1 (6.0) 0.1 (6.0)	ASTM D1876	-
WATER VAPOUR PERMEANCE:		Ng/Pa*s*m ² (perms)	< 3 (< 0.05)	ASTM E96	-
APPLICATION TEMPERATURE:		°C (°F)	≥ -12 (≥ 10)	-	-

* This is the ultimate elongation of the complete product. For the modified rubberized asphalt compound only the ultimate elongation is >200%.

See also Material Information Sheet – MIS # 1201

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.